

(19) 日本国特許庁 (J P)

再公表特許 (A 1)

(11) 国際公開番号

WO 99 / 63125

発行日 平成14年11月19日 (2002. 11. 19)

(43) 国際公開日 平成11年12月9日 (1999. 12. 9)

(51) Int.Cl.¹
 C 2 2 C 38/00
 38/22
 F 1 6 C 33/32
 33/62

識別記号
 3 0 1

F I
 C 2 2 C 38/00 3 0 1 T
 38/22
 F 1 6 C 33/32
 33/62

審査請求 有 予備審査請求 未請求 (全 23 頁)


出願番号 特願2000-552315(P2000-552315)
 (21) 国際出願番号 PCT / J P 99 / 02944
 (22) 国際出願日 平成11年6月2日 (1999. 6. 2)
 (31) 優先権主張番号 特願平10-156288
 (32) 優先日 平成10年6月4日 (1998. 6. 4)
 (33) 優先権主張国 日本 (J P)
 (31) 優先権主張番号 特願平10-268367
 (32) 優先日 平成10年9月22日 (1998. 9. 22)
 (33) 優先権主張国 日本 (J P)
 (81) 指定国 J P, U S

(71) 出願人 日本精工株式会社
 東京都品川区大崎1丁目6番3号
 (72) 発明者 山村 賢二
 神奈川県藤沢市鵜沼神明一丁目5番50号
 日本精工株式会社内
 (72) 発明者 田中 進
 神奈川県藤沢市鵜沼神明一丁目5番50号
 日本精工株式会社内
 (74) 代理人 弁理士 森 哲也 (外2名)

(54) 【発明の名称】 転がり軸受

(57) 【要約】

例えばHDDスピンドルモータユニットの軸(2)とハウジング(4)との間に組み込んで使用される玉軸受(3)として好適な、転がり軸受を提供する。そのため、内輪および外輪を形成する鉄鋼材料の組成を、0.80~1.20重量%、S1を0.60重量%以下、Mnを0.25重量%以下、Crを1.00~1.50重量%、Moを0.60~1.50重量%の範囲内とする。この鉄鋼材料で形成された内輪および外輪に焼入れ・焼き戻しを施して、残留オーステナイト量を0体積%に、表面硬さをHRC62以上にする。転がり軸受は、マルテンサイト系ステンレス鋼で形成され、焼入れ・焼き戻し後に窒化処理で表面に厚さ3 μ m以上の窒化層が形成された後に、仕上げ加工されて表面粗さ0.1 μ mRa以下になったものを使用する。



BEST AVAILABLE COPY

* NOTICES *

JPO and NCIPJ are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] An inner ring of spiral wound gasket, an outer ring of spiral wound gasket, and a rolling element at least any one As an alloy content, for C Si 0.80 to 1.20% of the weight 0.60 or less % of the weight, After being formed 0.25 or less % of the weight with the ferrous material which contains Cr 1.00 to 1.50% of the weight, and contains Mo by 0.60 – 1.50% of the weight of within the limits, Mn Anti-friction bearing characterized by giving hardening and tempering, and for the amount of retained austenites becoming 0 volume %, and surface hardness having become 62 or more HRC(s).

[Claim 2] Even if there are few inner rings of spiral wound gasket and outer rings of spiral wound gasket, either C as an alloy content 0.80 – 1.20 % of the weight, For Mn Cr 0.25 or less % of the weight 0.60 or less % of the weight 1.00 – 1.50 % of the weight, [Si] After being formed with the ferrous material which contains Mo by 0.60 – 1.50% of the weight of within the limits, hardening and tempering are given, the amount of retained austenites becomes 0 volume %, and surface hardness has become 62 or more HRC(s). A rolling element as an alloy content For Si Mn 0.3 to 1.5% of the weight 0.3 to 0.6% of the weight 0.3 – 1.7 % of the weight, [C] Cr is included and Mo is included 0.5 to 2.5% of the weight by 0.6 – 3.0% of the weight of within the limits. And anti-friction bearing characterized by being formed with the ferrous material whose content of O is 9 ppm or less, giving hardening and tempering after carbonitriding processing is performed, and for the amount of retained austenites becoming 0 volume %, and surface hardness having become 62 or more HRC(s).

[Claim 3] Even if there are few inner rings of spiral wound gasket and outer rings of spiral wound gasket, either C as an alloy content 0.80 – 1.20 % of the weight, For Mn Cr 0.25 or less % of the weight 0.60 or less % of the weight 1.00 – 1.50 % of the weight, [Si] After being formed with the ferrous material which contains Mo by 0.60 – 1.50% of the weight of within the limits Hardening and tempering are given, the amount of retained austenites becomes 0 volume %, and surface hardness has become 62 or more HRC(s). A rolling element Anti-friction bearing characterized by being formed with martensitic stainless steel, hardening and tempering being given, and nitriding treatment being performed behind, forming a nitrated case with a thickness of 3 micrometers or more in a front face, finish-machining after that, and surface roughness having become below 0.1micromRa.

[Claim 4] Even if there are few inner rings of spiral wound gasket and outer rings of spiral wound gasket, either C as an alloy content 0.80 – 1.20 % of the weight, For Mn Cr 0.25 or less % of the weight 0.60 or less % of the weight 1.00 – 1.50 % of the weight, [Si] It is anti-friction bearing characterized by forming the rolling element with the ceramics by giving hardening and tempering, and the amount of retained austenites becoming 0 volume %, and surface hardness having become 62 or more HRC(s) after being formed with the ferrous material which contains Mo by 0.60 – 1.50% of the weight of within the limits.

[Translation done.]